

Lehmann & Voss LUVOCOM® 1/CF/30/TF/13/SI/2/BK Polyamide 66, with carbon fiber, PTFE, lubricant modified, heat stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Carbon Fiber/PTFE Filled

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. High-strength and high-stiff parts; low coefficient of expansion. Improved friction and wear behaviour. Emergency running property. Electrically conductive, suitable for continuous discharging of statically generated electricity. High dimensionally stable precision parts with low warpage and narrow tolerance range. Gear parts for automotive appliances, control disks, cams, sliding elements. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1CF30TF13SI2BK-Polyamide-66-with-carbon-fiber-PTFE-lubricant-modified-heat-stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23Â°C/24h
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	220 MPa	31900 psi	
Elongation at Yield	2.0 %	2.0 %	
	2.5 %	2.5 %	flexural
Modulus of Elasticity	23.0 GPa	3340 ksi	
Flexural Strength	300 MPa	43500 psi	
Flexural Modulus	20.0 GPa	2900 ksi	
Charpy Impact Unnotched	4.00 J/cmÂ²	19.0 ft-lb/inÂ²	flatwise; ISO 179 1fU
	3.50 J/cmÂ²	16.7 ft-lb/inÂ²	ISO 179
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Charpy Impact, Notched	1.00 J/cmÂ²	4.76 ft-lb/inÂ²	ISO 179 1eA
	0.800 J/cmÂ²	3.81 ft-lb/inÂ²	ISO 179 eA
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Coefficient of Friction, Dynamic	0.10	0.10	

Mechanical Properties Static	Metric	English	Comments
------------------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear	14.0 Åµm/m-Å°C	7.78 Åµin/in-Å°F	DIN 53752
Thermal Conductivity	0.510 W/m-K	3.54 BTU-in/hr-Å²-Å°F	DIN 52612
Maximum Service Temperature, Air	120 Å°C	248 Å°F	
	160 Å°C	320 Å°F	short term
Deflection Temperature at 1.8 MPa (264 psi)	240 Å°C	464 Å°F	
Vicat Softening Point	255 Å°C	491 Å°F	DIN ISO 306

Electrical Properties	Metric	English	Comments
Surface Resistance	100 ohm	100 ohm	
Insulation Resistance	1000 ohm	1000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	290 Å°C	554 Å°F	mass temp
Nozzle Temperature	280 - 300 Å°C	536 - 572 Å°F	
Zone 1	290 - 310 Å°C	554 - 590 Å°F	
Zone 2	290 - 310 Å°C	554 - 590 Å°F	
Zone 3	290 - 310 Å°C	554 - 590 Å°F	
Mold Temperature	90.0 - 120 Å°C	194 - 248 Å°F	
Drying Temperature	75.0 Å°C	167 Å°F	Dehumidifying dryer
	@Time 21600 - 57600 sec	@Time 6.00 - 16.0 hour	
	105 Å°C	221 Å°F	Vacuum Dryer
	@Time 14400 - 21600 sec	@Time 4.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China