

Lehmann & Voss LUVOCOM® 50/CF/7/GF/20/TF/10/BK Polycarbonate, with carbon fiber, glass fiber and PTFE

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Carbon Fiber Reinforced

Material Notes:

Applications: Data processing machinery, precision engineering, film and photo industry, sporting and leisure goods, medical engineering. High-strength and high-stiff parts; low coefficient of expansion. Electrically conductive, suitable for continuous discharging of statically generated electricity. Improved friction and wear behaviour. Emergency running property. High dimensionally stable precision parts, even at elevated temperatures and narrow tolerance range. Body and duty parts in office equipment, gear wheels, grippers. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-50CF7GF20TF10BK-Polycarbonate-with-carbon-fiber-glass-fiber-and-PTFE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ISO 1183
Water Absorption	<= 0.20 %	<= 0.20 %	23Â°C/24h
Linear Mold Shrinkage	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	125 MPa	18100 psi	
Elongation at Yield	2.5 %	2.5 %	
	3.0 %	3.0 %	flexural
Modulus of Elasticity	9.00 GPa	1310 ksi	
Flexural Strength	185 MPa	26800 psi	
Flexural Modulus	8.00 GPa	1160 ksi	
Charpy Impact Unnotched	3.00 J/cmÂ²	14.3 ft-lb/inÂ²	flatwise; ISO 179 1fU
	2.50 J/cmÂ²	11.9 ft-lb/inÂ²	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	ISO 179
Charpy Impact, Notched	1.30 J/cmÂ²	6.19 ft-lb/inÂ²	ISO 179 1eA
	1.10 J/cmÂ²	5.23 ft-lb/inÂ²	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	ISO 179 eA
Coefficient of Friction, Dynamic	0.25	0.25	

Mechanical Properties Static	Metric	English	Comments
---	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear	25.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	13.9 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	DIN 53752
Thermal Conductivity	0.400 W/m-K	2.78 BTU-in/hr-ftÅ²-Å°F	DIN 52612
Maximum Service Temperature, Air	130 Å°C	266 Å°F	
	150 Å°C	302 Å°F	short term
Vicat Softening Point	160 Å°C	320 Å°F	DIN ISO 306
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Surface Resistance	$\leq 1.00\text{e}+8$ ohm	$\leq 1.00\text{e}+8$ ohm	
Insulation Resistance	$\leq 1.00\text{e}+9$ ohm	$\leq 1.00\text{e}+9$ ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	295 Å°C	563 Å°F	mass temp
Nozzle Temperature	290 - 310 Å°C	554 - 590 Å°F	
Zone 1	280 - 300 Å°C	536 - 572 Å°F	
Zone 2	290 - 310 Å°C	554 - 590 Å°F	
Zone 3	300 - 320 Å°C	572 - 608 Å°F	
Mold Temperature	80.0 - 120 Å°C	176 - 248 Å°F	
Drying Temperature	120 Å°C @Time 14400 - 21600 sec	248 Å°F @Time 4.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China