

Lehmann & Voss LUVOCOM® 50/GF/10/TF/18/SI/2/GY5 Polycarbonate, with glass fiber, PTFE, lubricant modified

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Glass + PTFE Filled

Material Notes:

Applications: Data processing machinery, precision engineering, film and photo industry, sporting and leisure goods, medical engineering. High-strength and high-stiff parts; low coefficient of expansion. Reduced moment of inertia compared with metal parts. Improved friction and wear behaviour. Emergency running property. High dimensionally stable precision parts, even at elevated temperatures and narrow tolerance range. Body and duty parts in office equipment, gear wheels, grippers. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-50GF10TF18SI2GY5-Polycarbonate-with-glass-fiber-PTFE-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ISO 1183
Water Absorption	<= 0.20 %	<= 0.20 %	23Â°C/24h
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	
Melt Flow	<= 12 g/10 min @Load 1.20 kg, Temperature 300 Â°C	<= 12 g/10 min @Load 2.65 lb, Temperature 572 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	70.0 MPa	10200 psi	
Elongation at Yield	4.0 %	4.0 %	
	4.5 %	4.5 %	flexural
Modulus of Elasticity	4.00 GPa	580 ksi	
Flexural Strength	100 MPa	14500 psi	
Flexural Modulus	3.50 GPa	508 ksi	
Charpy Impact Unnotched	4.00 J/cmÂ²	19.0 ft-lb/inÂ²	flatwise; ISO 179 1fU
	3.50 J/cmÂ² @Temperature -30.0 Â°C	16.7 ft-lb/inÂ² @Temperature -22.0 Â°F	ISO 179
Charpy Impact, Notched	2.50 J/cmÂ²	11.9 ft-lb/inÂ²	ISO 179 1eA
	2.00 J/cmÂ²	9.52 ft-lb/inÂ²	

Mechanical Properties	Metric @ Temperature -30.0 Â°C	English @ Temperature -22.0 Â°F	ISO 179 eA Comments
Coefficient of Friction, Dynamic	0.15	0.15	
Coefficient of Friction, Static	0.12	0.12	

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	DIN 53752
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ftÂ²- Â°F	DIN 52612
Maximum Service Temperature, Air	130 Â°C	266 Â°F	
	150 Â°C	302 Â°F	short term
Vicat Softening Point	160 Â°C	320 Â°F	DIN ISO 306
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	295 Â°C	563 Â°F	mass temp
Nozzle Temperature	290 - 310 Â°C	554 - 590 Â°F	
Zone 1	280 - 300 Â°C	536 - 572 Â°F	
Zone 2	290 - 310 Â°C	554 - 590 Â°F	
Zone 3	300 - 320 Â°C	572 - 608 Â°F	
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	
Drying Temperature	120 Â°C @Time 14400 - 21600 sec	248 Â°F @Time 4.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	telegrey 4	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China