

Lehmann & Voss LUVOCOM® 65-8347/RD PP-copolymer, with carbon fiber

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Applications: Office communication.Strong, stiff parts.Electrically conductive, suitable for continuous discharging of statically generated electricity.Low warpage.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-65-8347RD-PP-copolymer-with-carbon-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ISO 1183
Water Absorption	<= 0.30 %	<= 0.30 %	23Â°C/24h
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	45.0 MPa	6530 psi	
Elongation at Yield	1.0 %	1.0 %	
	1.3 %	1.3 %	flexural
Modulus of Elasticity	7.00 GPa	1020 ksi	
Flexural Strength	65.0 MPa	9430 psi	
Flexural Modulus	5.50 GPa	798 ksi	
Charpy Impact Unnotched	1.00 J/cmÂ²	4.76 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 Â°C	212 Â°F	
	130 Â°C	266 Â°F	short term
Vicat Softening Point	80.0 Â°C	176 Â°F	DIN ISO 306

Electrical Properties	Metric	English	Comments
Insulation Resistance	<= 10000 ohm	<= 10000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	230 - 260 Â°C	446 - 500 Â°F	mass temp

Nozzle Temperature Processing Properties	220 - 250 Â°C Metric	428 - 482 Â°F English	Comments
Zone 1	220 - 250 Â°C	428 - 482 Â°F	
Zone 2	220 - 250 Â°C	428 - 482 Â°F	
Zone 3	230 - 260 Â°C	446 - 500 Â°F	
Mold Temperature	40.0 - 80.0 Â°C	104 - 176 Â°F	
Drying Temperature	70.0 - 95.0 Â°C @Time 7200 - 14400 sec	158 - 203 Â°F @Time 2.00 - 4.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	purple red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China