

Lendell Parapet EH-1000 PMMA, Extrusion

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, Extruded

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lendell-Parapet-EH-1000-PMMA-Extrusion.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Water Absorption	0.30 %	0.30 %	ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ASTM D955
Melt Index of Compound	1.2 g/10 min @Load 3.80 kg, Temperature 230 Â°C	1.2 g/10 min @Load 8.38 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	97	97	ASTM D785
Tensile Strength, Yield	73.5 MPa	10700 psi	ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Flexural Yield Strength	118 MPa	17100 psi	ASTM D790
Flexural Modulus	3.33 GPa	484 ksi	ASTM D790
Izod Impact, Notched	0.157 J/cm	0.294 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	92.0 Â°C	198 Â°F	unannealed; ASTM D648
	101 Â°C	214 Â°F	annealed; ASTM D648
Vicat Softening Point	111 Â°C	232 Â°F	ASTM D1525
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ASTM D542
Haze	0.30 %	0.30 %	ASTM D1003
Transmission, Visible	93 %	93 %	ASTM D1003

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China