

Loctite® 410 Toughened Ethyl Cyanoacrylate Bonding Adhesive

Category: Polymer, Adhesive, Thermoset, Acrylic/Cyanoacrylate Adhesive

Material Notes:

Cyanoacrylate Bonding AdhesivesLoctite® technology has made the productivity promises of cyanoacrylate adhesives a reality with the industry's widest selection of high-performance, application-specific, instant adhesives. Loctite® Instant Adhesives are available in a variety of viscosities, cure speeds, gap-filling capability and substrate compatibility. The ultra high-performance PRISM® family offers additional products that surpass the most stringent demands, including toughened formulations, low odor and low blooming products, surface insensitive and thermally resistant formulations.Loctite® 410 Toughened Ethyl Cyanoacrylate Bonding Adhesive Cure Type: 5960 Bonding Type: Cyanoacrylate Typical Use: Gap filling

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loctite-410-Toughened-EthylCyanoacrylate-Bonding-Adhesive.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|---------------|----------|
| Density | 1.07 g/cc | 0.0387 lb/in³ | |
| Viscosity | 3500 cP | 3500 cP | |

| Mechanical Properties | Metric | English | Comments |
|------------------------|----------|----------|--------------------|
| Adhesive Bond Strength | 22.1 MPa | 3200 psi | Grit blasted steel |

| Thermal Properties | Metric | English | Comments | |
|----------------------------------|----------|----------|----------|--|
| Maximum Service Temperature, Air | 107°C | 225 °F | | |
| Minimum Service Temperature, Air | -53.9 °C | -65.0 °F | | |

| Processing Properties | Metric | English | Comments |
|-----------------------|----------|-------------|-----------------------------------|
| Cure Time | 1.50 min | 0.0250 hour | |
| | 1440 min | 24.0 hour | Full Cure; Varies with substrates |

| Descriptive Properties | Value | Comments |
|------------------------|-----------|----------|
| Color | Black | |
| Gap Fill | 0.008 in. | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842



Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China