

Loctite® 420 General Purpose Ethyl Cyanoacrylate Bonding Adhesive

Category: Polymer, Adhesive, Thermoset, Acrylic/Cyanoacrylate Adhesive

Material Notes:

Cyanoacrylate Bonding AdhesivesLoctite® technology has made the productivity promises of cyanoacrylate adhesives a reality with the industry's widest selection of high-performance, application-specific, instant adhesives. Loctite® Instant Adhesives are available in a variety of viscosities, cure speeds, gap-filling capability and substrate compatibility. The ultra high-performance PRISM® family offers additional products that surpass the most stringent demands, including toughened formulations, low odor and low blooming products, surface insensitive and thermally resistant formulations.Loctite® 420 General Purpose Ethyl Cyanoacrylate Bonding Adhesive Bonding Type: Cyanoacrylate Commercial item std. A-A-3097 Type II, Class 1 Typical Use: Wicking type plastic bonder

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loctite-420-General-Purpose-EthylCyanoacrylate-Bonding-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in³	
Viscosity	2.0 cP	2.0 cP	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	20.0 MPa	2900 psi	Grit blasted steel

Thermal Properties	Metric	English	Comments	
Maximum Service Temperature, Air	82.2 °C	180 °F		
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F		

Processing Properties	Metric	English	Comments
Cure Time	0.300 min	0.00500 hour	
	1440 min	24.0 hour	Full Cure; Varies with substrates

Descriptive Properties	Value	Comments
Color	Clear	
Gap Fill	0.002 in.	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842



Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China