

Loctite® 573 Semi-rigid Cure Anaerobic Sealant

Category : Polymer , Adhesive , Thermoset

Material Notes:

Anaerobic Gasketing Loctite® 573 Semi-rigid Cure Anaerobic Sealant Recommended Primer: 7649 (N). Typical Use: Slow curing for extended assembly operations

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loctite-573-Semi-rigid-CureAnaerobic-Sealant.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in³	
Viscosity	19000 - 60000 cP	19000 - 60000 cP	Thixotropic

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 360 min	1.00 - 6.00 hour	Full Cure; Primed
	360 - 2880 min	6.00 - 48.0 hour	Full Cure; Unprimed

Descriptive Properties	Value	Comments
Color	Green	
Gap Fill	0.010 in.	Unprimed
	0.02 in.	Primed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China