

## Lord Adhesives 5019 Fast Setting, High Elasticity, High Viscosity Ethyl Cyanoacrylate Adhesive

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

### Material Notes:

Lord Cyanoacrylate Adhesives Lord® Cyanoacrylate Adhesives were developed for production situations requiring instant bonds and immediate handling strength, particularly when bonding rubber, metals and plastics. Lord Cyanoacrylate Adhesives offer these benefits:

Instant Cure. Lord Cyanoacrylate Adhesives develop strong bonds with setting times ranging from 5 to 130 seconds. Ease of Use. Lord Cyanoacrylate Adhesives are one-component systems that facilitate set-up and minimize production costs. Good Environmental Resistance. Lord Cyanoacrylate Adhesives offer excellent resistance to weathering and aging. Lord Adhesives 5019 Fast Setting, High Elasticity, High Viscosity Ethyl Cyanoacrylate Adhesive Fast setting. High viscosity. High elasticity. Gap filling. Colorless. Temperature resistance to 250°F (121°C). Especially suitable for bonding dissimilar and porous materials. Will qualify for USP Class IV approvals. MIL-A-46050C Type II, Class 3 Approved.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lord-Adhesives-5019-Fast-Setting-High-Elasticity-High-Viscosity-Ethyl-Cyanoacrylate-Adhesive.php](http://www.lookpolymers.com/polymer_Lord-Adhesives-5019-Fast-Setting-High-Elasticity-High-Viscosity-Ethyl-Cyanoacrylate-Adhesive.php)

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0400 lb/in <sup>3</sup>	
Viscosity	2400 cP	2400 cP	

Processing Properties	Metric	English	Comments
Cure Time	0.100 - 0.167 min	0.00167 - 0.00278 hour	Plastic set time
	0.417 - 0.583 min	0.00694 - 0.00972 hour	Metal set time

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China