

Lord Adhesives 6900 Medium Viscosity, Low Odor, Low Bloom Butyl Cyanoacrylate Adhesive

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

Material Notes:

Lord Cyanoacrylate Adhesives Lord® Cyanoacrylate Adhesives were developed for production situations requiring instant bonds and immediate handling strength, particularly when bonding rubber, metals and plastics. Lord Cyanoacrylate Adhesives offer these benefits: Instant Cure. Lord Cyanoacrylate Adhesives develop strong bonds with setting times ranging from 5 to 130 seconds. Ease of Use. Lord Cyanoacrylate Adhesives are one-component systems that facilitate set-up and minimize production costs. Good Environmental Resistance. Lord Cyanoacrylate Adhesives offer excellent resistance to weathering and aging. Lord Adhesives 6900 Medium Viscosity, Low Odor, Low Bloom Butyl Cyanoacrylate Adhesive Medium viscosity. Low Odor. Low Bloom. For bonding plastic and elastomers where high resistance to chlorosis and blooming is important. MIL-A-46050C Type IV, Class 2 Approved.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lord-Adhesives-6900-Medium-Viscosity-Low-Odor-Low-Bloom-Butyl-Cyanoacrylate-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0382 lb/in ³	
Viscosity	90 cP	90 cP	

Processing Properties	Metric	English	Comments
Cure Time	0.0500 - 0.0833 min	0.000833 - 0.00139 hour	Rubber set time
	0.100 - 0.133 min	0.00167 - 0.00222 hour	Plastic set time

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China