

Loxim 330 01HSL Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled , Nylon 6, Glass Fiber Filled, Flame Retardant

Material Notes:

Information provided by Loxim Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loxim-330-01HSL-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D1299

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	160 MPa	23200 psi	ASTM D683
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	ASTM D638
Flexural Modulus	8.00 GPa	1160 ksi	ASTM D790
Izod Impact, Notched	1.40 J/cm	2.62 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	200 Â°C	392 Â°F	ASTM D1525, HDT Method B

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China