

Lubrizol Advanced Materials PEARLBOND® 522 Linear Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

Pearlbond® 522 is a linear, polycaprolactone-copolyester polyurethane, supplied in form of white spherical granules with a very high crystallization rate and a very high thermoplasticity level. Application: Pearlbond® 522 can be added to formulations of REACTIVE POLYURETHANE HOT-MELTS (HMPUR), in order to improve the crystallisation speed.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-PEARLBOND-522-Linear-Thermoplastic-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 2781
Viscosity	4.90e+6 cP @Temperature 130 °C	4.90e+6 cP @Temperature 266 °F	Melt; ISO 1133
Melt Flow	105 - 160 g/10 min @Load 2.16 kg, Temperature 170 °C	105 - 160 g/10 min @Load 4.76 lb, Temperature 338 °F	ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	65.0 - 69.0 °C	149 - 156 °F	MQSA 70 A

Chemical Properties	Metric	English	Comments
Total Base Number	<= 3.0	<= 3.0	mg KOH/g; MQSA 47 A

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.15 %	<= 0.15 %	MQSA 44

Descriptive Properties	Value	Comments
Crystallization rate (minutes)	9 - 11	MQSA 12 B
Thermoplasticity	Very high	MQSA 68 A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China