

## Lubrizol ESTANE® 58213 Ester Based Thermoplastic Polyurethane (European Grade)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

### Material Notes:

**Description:** Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs. **Benefits of Estane® TPU:** Outstanding Abrasion and Wear ResistanceExcellent Low Temperature FlexibilitySuperior Toughness and DurabilityEase of Processing and Manufacturing FlexibilityColorability and Paintability with no adhesion promoter**Applications:** Film & SheetFabric coating & melt coatingWire & CableHose, Tube & ProfileCustom moldingCustom compoundingAutomotive interior/chassis and exterior painted trim**Specific Notes for this Material:** Excellent compatibility with PVC, clear, soft touch for overmolding Information provided by Noveon, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-ESTANE-58213-Ester-Based-Thermoplastic-Polyurethane-European-Grade.php](http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-58213-Ester-Based-Thermoplastic-Polyurethane-European-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	DIN 53479

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76	76	DIN 53505
Tensile Strength, Ultimate	25.0 MPa	3630 psi	DIN 53504
Elongation at Break	700 %	700 %	DIN 53504
50% Modulus	0.00270 GPa	0.392 ksi	DIN 53504
100% Modulus	0.00320 GPa	0.464 ksi	DIN 53504
300% Modulus	0.00490 GPa	0.711 ksi	DIN 53504
Tear Strength	45.0 kN/m	257 pli	DIN 53515
Abrasion	70	70	mm<sup>3</sup>; DIN 53516

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-70.0 °C	-94.0 °F	DIN 53546

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**