

Lubrizol Estane® 2103-90AENH Film Grade Thermoplastic Polyurethane Elastomer

Category : Polymer , Film , Thermoplastic , Elastomer , TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

Material Notes:

Formerly Pellethane Feature: NSF Standard 61 Certified, FDA Compliance Available in Americas, Europe, Middle East, Africa, India and Asia Data provided by Lubrizol. Lubrizol acquired the Pellethane product line from Dow in 2009.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Estane-2103-90AENH-Film-Grade-Thermoplastic-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0070 - 0.010 cm/cm	0.0070 - 0.010 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	ASTM D955
Melt Flow	9.0 g/10 min @Load 8.70 kg, Temperature 224 °C	9.0 g/10 min @Load 19.2 lb, Temperature 435 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	ASTM D2240
Hardness, Shore D	47	47	ASTM D2240
Tensile Strength, Ultimate	48.2 MPa	6990 psi	ASTM D412
Elongation at Break	560 %	560 %	ASTM D412
50% Modulus	0.00620 GPa	0.899 ksi	ASTM D412
100% Modulus	0.00900 GPa	1.31 ksi	ASTM D412
300% Modulus	0.0172 GPa	2.49 ksi	ASTM D412
Tear Strength	126 kN/m	719 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	50	50	H-22 wheel (coarser), 1000g; ASTM D1044
Compression Set	25 %	25 %	22 hrs. @ 77°F (25°C); ASTM D395, Method B
	40 % @Temperature 70.0 °C	40 % @Temperature 158 °F	22 hrs.; ASTM D395, Method B
Tensile Set	60 %	60 %	Elongation Set After Break; ASTM D412

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	155 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	86.1 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM D696
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Vicat Softening Point	90.0 $^{\circ}\text{C}$	194 $^{\circ}\text{F}$	120 $^{\circ}\text{C}/\text{hr}$, 9.8N; ASTM D1525
Glass Transition Temp, Tg	-34.0 $^{\circ}\text{C}$	-29.2 $^{\circ}\text{F}$	DSC

Processing Properties	Metric	English	Comments
Melt Temperature	188 - 204 $^{\circ}\text{C}$	370 - 399 $^{\circ}\text{F}$	Extrusion
	193 - 210 $^{\circ}\text{C}$	379 - 410 $^{\circ}\text{F}$	Molding
Mold Temperature	16.0 - 60.0 $^{\circ}\text{C}$	60.8 - 140 $^{\circ}\text{F}$	
Drying Temperature	88.0 - 104 $^{\circ}\text{C}$	190 - 219 $^{\circ}\text{F}$	air dew point $<-40^{\circ}\text{C}$

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China