

Lubrizol Isoplast® 101LGF60NAT Engineering Thermoplastic Polyurethane Resin

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Glass Fiber Reinforced

Material Notes:

Available in Americas, Europe, Middle East, Africa, India and Asia
Data provided by Lubrizol
Lubrizol acquired the Isoplast product line from Dow in 2009.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Isoplast-101LGF60NAT-Engineering-Thermoplastic-Polyurethane-Resin.php

Physical Properties	Metric	English	Comments
Density	1.71 g/cc	0.0618 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	227 MPa	32900 psi	ASTM D638
Tensile Strength, Yield	227 MPa	32900 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ASTM D638
Tensile Modulus	17.0 GPa	2470 ksi	ASTM D638
Flexural Strength	393 MPa	57000 psi	ASTM D790
Flexural Modulus	15.0 GPa	2180 ksi	ASTM D790
Izod Impact, Unnotched	8.54 J/cm	16.0 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 °C	@Thickness 0.126 in, Temperature 73.4 °F	
	8.54 J/cm	16.0 ft-lb/in	ASTM D256
	@Thickness 81.3 mm, Temperature -40.0 °C	@Thickness 3.20 in, Temperature -40.0 °F	
Dart Drop, Total Energy	25.0 J	18.4 ft-lb	ASTM D3767
	@Temperature -29.0 °C	@Temperature -20.2 °F	
	29.0 J	21.4 ft-lb	ASTM D3767
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
	11.0 µm/m-°C	6.11 µin/in-°F	

<small>CTE linear</small> Thermal Properties	Metric @ Temperature 20.0 °C	English @ Temperature 68.0 °F	ASTM D 698 Comments
Deflection Temperature at 1.8 MPa (264 psi)	127 °C	261 °F	Unannealed; ASTM D648
	127 °C	261 °F	Annealed; ASTM D648
Vicat Softening Point	186 °C	367 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Melt Temperature	240 - 260 °C	464 - 500 °F	
Mold Temperature	65.0 - 90.0 °C	149 - 194 °F	
Drying Temperature	80.0 - 100 °C	176 - 212 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China