

Lucite International Colacryl ® P2601 Specialty Polystyrene Resin

Category: Polymer, Thermoplastic, Polystyrene (PS)

Material Notes:

Cross-linked polystyrene resins have much higher thermal stability than conventional thermoplastic acrylic resins. Colacryl® P2601 is stable up to around 300°C.Suggested Uses:This product is usually used as a filler for investment casting waxes. The product may also be used as a texturing agent for surface coatings for use in flammable atmospheres.Information provided by Lucite International

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucite-International-Colacryl-P2601-Specialty-Polystyrene-Resin.php

Physical Properties	Metric	English	Comments
Particle Size	35 μm	35 μm	
Ash	<= 0.050 %	<= 0.050 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	300 °C	572 °F	

Processing Properties	Metric	English	Comments
Moisture Content	0.50 %	0.50 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China