

Lucobit Lucofin® 1410 Polyolefin TPO Granules, Grey

Category: Polymer, Thermoplastic, Polyolefin

Material Notes:

Lucofin is a colored, highly stabilized, bitumen-free TPO raw material based on polyolefins. Lucofin products display excellent tear resistance, flexibility, and weathering resistance. Lucofin exhibits good toughness, superior biaxial stretchability, and flexibility even at low temperatures. It is insensitive to stress cracking and notch effects. Special stabilization provides good resistance to heat ageing and UV radiation. Lucofin is thus to a large extent resistant to weathering and ageing. Applications:• Roofing and swimming pool membranes• Construction profiles and water stops• Injection molded parts in the building sectorInformation provided by Lucobit AG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucobit-Lucofin-1410-Polyolefin-TPO-Granules-Grey.php

Physical Properties	Metric	English	Comments	
Density	0.990 g/cc	0.0358 lb/in³	ISO 1183	
Melt Flow	8.0 g/10 min	8.0 g/10 min		
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	ISO 1133	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	ISO 868

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	<= -45.0 °C	<= -49.0 °F	Low Temperature Flexural Test; EN 495-5

Processing Properties	Metric	English	Comments
Processing Temperature	150 - 180 °C	302 - 356 °F	Profiles
	160 - 230 °C	320 - 446 °F	Membranes
	160 - 240 °C	320 - 464 °F	Coatings
Melt Temperature	160 - 220 °C	320 - 428 °F	
Mold Temperature	10.0 - 40.0 °C	50.0 - 104 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058



Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China