

Lushan M-10H Adhesive Resin for Multi-layer Sausage Casing film

Category : Polymer , Adhesive , Film , Thermoplastic , Polypropylene (PP)

Material Notes:

Adhesive resin Lushan series for sausages casing film is anhydride-modified polyethylene product and is available in pellet form. Adhesive resin Lushan series for sausages casing film is designed for multi-layer sausages casing films composed of polyethylene (PE) and EVOH or PA. Lushan adhesive resins are based on LLDPE and are highly stabilized for multi-layer sausages casing films application in three layer casing film like PA/Tie layer resin/PA and five layer casing film like PA/Tie layer resin/PA. Lushan casing film adhesive resin created super adhesion between EVOH and PE while maintaining an excellent processability equivalent to that of common LLDPE. Adhesive resin Lushan series for food package complies with FDA 21CFR175.105 and suitable for indirect food contact.Application: Colored FilmInformation provided by Lushan

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lushan-M-10H-Adhesive-Resin-for-Multi-layer-Sausage-Casing-film.php

| Physical Properties | Metric | English | Comments | |
|---------------------------|--------------|---------------|------------|--|
| Density | 0.920 g/cc | 0.0332 lb/in³ | ASTM D1505 | |
| Melt Index of Compound | 1.8 g/10 min | 1.8 g/10 min | ASTM D1238 | |
| | | | | |
| Mechanical Properties | Metric | English | Comments | |
| Tensile Strength at Break | 13.0 MPa | 1890 psi | ASTM D638 | |
| Elongation at Break | 500 % | 500 % | ASTM D638 | |
| | | | | |
| Thermal Properties | Metric | English | Comments | |
| Melting Point | 121 °C | 250 °F | ASTM D2117 | |
| Vicat Softening Point | 65.0 °C | 149 °F | ASTM D1525 | |
| Brittleness Temperature | -70.0 °C | -94.0 °F | ASTM D746 | |

| Descriptive Properties | Value | Comments |
|------------------------|-----------------------|----------|
| Appearance | Transparent particles | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers



Address : United North Road 215, Fengxian District, Shanghai City, China