

LyondellBasell Lupolen® 5361 A HDPE, Blow Molding Grade

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

Material Notes:

Easy-to-process blow molding grade for stackable canisters (up to 60 l), used for packing surface-active liquids, laundry and dishwashing detergents, disinfectants, drums (up to 220 l) for various surface-active liquids and aggressive chemicals. Data was collected by ISO methods and originally provided by BASF. The Lupolen® product line is now produced by Basell.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Lupolen-5361-A-HDPE-Blow-Molding-Grade.php

Physical Properties	Metric	English	Comments
Density	0.952 g/cc	0.0344 lb/in ³	
Water Absorption	0.010 %	0.010 %	
Moisture Absorption at Equilibrium	0.010 %	0.010 %	
Melt Flow	0.10 g/10 min @Load 2.16 kg, Temperature 190 °C	0.10 g/10 min @Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.0 MPa	3770 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	9.0 %	9.0 %	
Tensile Modulus	1.00 GPa	145 ksi	
Tensile Impact Strength	230 kJ/m ²	109 ft-lb/in ²	
Tensile Creep Modulus, 1 hour	380 MPa	55100 psi	
Tensile Creep Modulus, 1000 hours	270 MPa	39200 psi	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	155 µm/m-°C @Temperature 20.0 °C	86.1 µin/in-°F @Temperature 68.0 °F	
Melting Point	133 °C	271 °F	
Deflection Temperature at 0.46 MPa (66 psi)	76.0 °C	169 °F	
Deflection Temperature at 1.8 MPa	45.0 °C	113 °F	

(264 psi) Thermal Properties	Metric	English	Comments
Vicat Softening Point	80.0 Å°C	176 Å°F	
Flammability, UL94	HB	HB	
	@Thickness 0.400 mm	@Thickness 0.0157 in	
Oxygen Index	17 %	17 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	2.4	2.4	
	@Frequency 100 Hz	@Frequency 100 Hz	
	2.4	2.4	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	150 kV/mm	3810 kV/in	
Dissipation Factor	0.00020	0.00020	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.00020	0.00020	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China