

## LyondellBasell Montell HB312CM UHMW Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

### Material Notes:

**Key Features:** ultrahigh molecular weight polyethylene resin, excellent abrasion resistance, high impact strength, low coefficient of friction, good chemical resistance, low odor and taste transfer, FDA acceptable

**Applications:** wear surfaces in pulp and paper process, material handling and packaging equipment, food and beverage processing systems, impact and abrasion resistant parts for mining and solid waste handling, marine fendering, battery separators

**Meets FDA requirements in 21 CFR 177.1520 for all food contact, including cooking applications.**

**Description:** HB312CM ultrahigh molecular weight polyethylene resin is for use in compression molding, solution and ram extrusion processes. It is supplied in a fine powder form with calcium stearate added as a dry flow processing aid. This resin meets FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for all food contact, including cooking applications. All ingredients meet the chemical registration requirements of TSCA and DSL.

Information provided by Montell Polyolefins. LyondellBasell is the successor company to Montell.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LyondellBasell-Montell-HB312CM-UHMW-Polyethylene.php](http://www.lookpolymers.com/polymer_LyondellBasell-Montell-HB312CM-UHMW-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in <sup>3</sup>	ASTM D792
Apparent Bulk Density	0.490 - 0.510 g/cc	0.0177 - 0.0184 lb/in <sup>3</sup>	ASTM D792
Viscosity Test	2000 cm <sup>3</sup> /g	2000 cm <sup>3</sup> /g	Intrinsic; ASTM D4020

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68	68	ASTM D2240
Tensile Strength, Ultimate	40.0 MPa	5800 psi	ASTM D638
Tensile Strength, Yield	19.0 MPa	2760 psi	ASTM D638
Elongation at Break	380 %	380 %	ASTM D638
Elongation at Yield	13 %	13 %	ASTM D638
Flexural Modulus	0.750 GPa	109 ksi	1% secant at 0.05 in/min; ASTM D790B
Izod Impact, Notched	NB	NB	ASTM D256
Abrasion	11	11	% Abrasion Index; Montell P116 Test

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**