

LyondellBasell Montell HB320CM UHMW Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Key Features: ultrahigh molecular weight polyethylene resin, excellent abrasion resistance, high impact strength, low coefficient of friction, good chemical resistance, low odor and taste transfer, FDA acceptable

Applications: wear surfaces in pulp and paper process, material handling and packaging equipment, food and beverage processing systems, impact and abrasion resistant parts for mining and solid waste handling, marine fendering, battery separators

Meets FDA requirements in 21 CFR 177.1520 for all food contact, including cooking applications.

Description: HB320Cm ultrahigh molecular wight polyethylene resin has an average molecular weight range between 4 and 5 million. This polymer is for use in compression moldind, solution and ram extrusion processes. It is supplied in a fine powder form with calcium stearate added as a dry flow processing aid. This resin meets FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for all food contact, including cooking applications. All indgredients meet the chemical regristration requirments of TSCA and DSL.

Information provided by Montell Polyolefins. LyondellBasell is the successor company to Montell.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Montell-HB320CM-UHMW-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	ASTM D792
Apparent Bulk Density	0.490 - 0.510 g/cc	0.0177 - 0.0184 lb/in ³	ASTM D792
Viscosity Test	2800 cm ³ /g	2800 cm ³ /g	Intrinsic; ASTM D4020

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68	68	ASTM D2240
Tensile Strength, Ultimate	40.0 MPa	5800 psi	ASTM D638
Tensile Strength, Yield	19.0 MPa	2760 psi	ASTM D638
Elongation at Break	320 %	320 %	ASTM D638
Elongation at Yield	13 %	13 %	ASTM D638
Flexural Modulus	0.750 GPa	109 ksi	1% secant at 0.05 in/min; ASTM D790B
Izod Impact, Notched	NB	NB	ASTM D256
Abrasion	9.0	9.0	% Abrasion Index; Montell P116 Test

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China