

Magyar Aluminum 6N Gallium

Category : Pure Element

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Magyar-Aluminum-6N-Gallium.php

Component Elements Properties	Metric	English	Comments
Aluminum, Al	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Antimony, Sb	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Bismuth, Bi	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Boron, B	$\leq 1.0e-7 \%$	$\leq 1.0e-7 \%$	
Calcium, Ca	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Chlorine, Cl	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Chromium, Cr	$\leq 1.0e-7 \%$	$\leq 1.0e-7 \%$	
Copper, Cu	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Gallium, Ga	$\geq 100 \%$	$\geq 100 \%$	
Indium, In	$\leq 1.0e-6 \%$	$\leq 1.0e-6 \%$	
Iron, Fe	$\leq 1.0e-6 \%$	$\leq 1.0e-6 \%$	
Lead, Pb	$\leq 0.0000015 \%$	$\leq 0.0000015 \%$	
Magnesium, Mg	$\leq 3.0e-7 \%$	$\leq 3.0e-7 \%$	
Manganese, Mn	$\leq 1.0e-7 \%$	$\leq 1.0e-7 \%$	
Mercury, Hg	$\leq 0.0000020 \%$	$\leq 0.0000020 \%$	
Nickel, Ni	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Phosphorous, P	$\leq 2.0e-7 \%$	$\leq 2.0e-7 \%$	
Platinum, Pt	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Silicon, Si	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Sodium, Na	$\leq 3.0e-7 \%$	$\leq 3.0e-7 \%$	
Sulfur, S	$\leq 5.0e-7 \%$	$\leq 5.0e-7 \%$	
Tellurium, Te	$\leq 1.0e-6 \%$	$\leq 1.0e-6 \%$	

Tin, Sn Component Elements Properties	<= 1.0e-6 % Metric	<= 1.0e-6 % English	Comments
Titanium, Ti	<= 2.0e-7 %	<= 2.0e-7 %	
Tungsten, W	<= 1.0e-6 %	<= 1.0e-6 %	
Vanadium, V	<= 1.0e-7 %	<= 1.0e-7 %	
Zinc, Zn	<= 5.0e-7 %	<= 5.0e-7 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China