

Mallard Creek Polymers ROVENE® 6066 Styrene-Acrylic Latex

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

Material Notes:

Applications: Rovene® 6066 is specifically designed for formulation of binder systems for moldable and self supporting composites. Its molecular weight allows formulation latitude for many "stiff-hand" binder formulations including application areas such as nonwovens, paper saturation and textiles. Rovene® 6066 is also recommended as a hand modifier in formulations where a little extra stiffness is desired. **Storage and Handling:** Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 6066 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-ROVENE-6066-Styrene-Acrylic-Latex.php

Physical Properties	Metric	English	Comments
Solids Content	49 - 51 %	49 - 51 %	
Particle Size	0.16 µm	0.16 µm	
pH	6.0 - 7.0	6.0 - 7.0	
Brookfield Viscosity	400 cP	400 cP	#2/20 rpm

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	97.0 °C	207 °F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China