

Mallard Creek Polymers Rovene® 5499 Styrene-Butadiene Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

Material Notes:

Rovene® 5499 is a styrene-butadiene emulsion that was developed as an ink vehicle for TPO based wall coverings. More specifically it can be formulated for metallic ink vehicles. Rovene® 5499 provides inks with excellent adhesion to TPO wall covering substrates and good alkaline resistance properties. Storage and Handling: Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 5499 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-5499-Styrene-Butadiene-Emulsion.php

Physical Properties	Metric	English	Comments
Solids Content	52 - 53 %	52 - 53 %	
Particle Size	0.16 µm	0.16 µm	
pH	7.0 - 7.8	7.0 - 7.8	
Brookfield Viscosity	<= 1000 cP	<= 1000 cP	#20/200

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	0.000 °C	32.0 °F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China