

Mallard Creek Polymers Rovene® 6065 Styrene-Acrylic Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Applications: Rovene® 6065 is a tough, durable nonwoven binder intended to provide improved stiffness and strength. Rovene® 6065 was specifically designed to perform in formaldehyde-free systems. This binder can be applied with conventional application systems and while focused on polyester markets, can be used with all types of fibers.
Storage and Handling: Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 6065 Material Safety Data Sheet before handling, storing, or using this product.
Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-6065-Styrene-Acrylic-Emulsion.php

Physical Properties	Metric	English	Comments
Solids Content	50 - 52 %	50 - 52 %	
Particle Size	0.14 µm	0.14 µm	
pH	6.0 - 7.5	6.0 - 7.5	
Brookfield Viscosity	<= 500 cP	<= 500 cP	#20/200

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	48.0 °C	118 °F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China