

Mapal Plastics Maplon Type O Polypropylene Sheet

Category : Polymer , Film , Thermoplastic , Polypropylene (PP) , Polypropylene, Sheet/Thermoforming Grade

Material Notes:

Properties: Corona treated on both sides for offset and screen printing, Extended shelf life, Low stress whitening, Suitable for die cutting
Applications: Stationery products, Offset printed item

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mapal-Plastics-Maplon-Type-O-Polypropylene-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	
Thickness	1000 microns	39.4 mil	
Surface Tension	>= 48 dynes/cm	>= 48 dynes/cm	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	26.0 MPa @Temperature 23.0 Å°C	3770 psi @Temperature 73.4 Å°F	ASTM D638
Film Tensile Strength at Yield, TD	23.0 MPa @Temperature 23.0 Å°C	3340 psi @Temperature 73.4 Å°F	ASTM D638
Film Elongation at Break, MD	>= 650 % @Temperature 23.0 Å°C	>= 650 % @Temperature 73.4 Å°F	ASTM D638
Film Elongation at Break, TD	>= 300 % @Temperature 23.0 Å°C	>= 300 % @Temperature 73.4 Å°F	ASTM D638
Film Elongation at Yield, MD	23 % @Temperature 23.0 Å°C	23 % @Temperature 73.4 Å°F	ASTM D638
Film Elongation at Yield, TD	19 % @Temperature 23.0 Å°C	19 % @Temperature 73.4 Å°F	ASTM D638
Modulus of Elasticity	0.300 GPa @Temperature 23.0 Å°C	43.5 ksi @Temperature 73.4 Å°F	MD/TD; ASTM D638
	1.00 J/cm	1.87 ft-lb/in	

Izod Impact Notched Mechanical Properties	Metric @Thickness 3.20 mm, Temperature 0.000 Â°C	English @Thickness 0.126 in, Temperature 32.0 Â°F	ASTM D256 Comments
	4.20 J/cm	7.87 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Â°C	@Thickness 0.126 in, Temperature 73.4 Â°F	
Dart Drop, Total Energy	5.50 J	4.06 ft-lb	ASTM D1709-85
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Dart Drop Total Energy	55.0 J/cm	0.103 ft-lb/mil	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	140 Â°C	284 Â°F	ASTM D1525
Heat Distortion Temperature	80.0 Â°C	176 Â°F	ASTM D648

Descriptive Properties	Value	Comments
Color	Mapal Color Catalogue No. 520002	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China