

Mar-Bal MB2000-8 Thermoset Polyester Composite Molding Compound

Category : Polymer , Thermoset , Polyester, TS , Thermoset Polyester Glass Filled BMC

Material Notes:

An excellent flame and track resistant material with excellent electrical and mechanical properties. Good dielectric strength and low shrink for close dimensional control. Mar-Bal standard grades can be injection, compression and transfer molded. Information provided by Mar-Bal, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mar-Bal-MB2000-8-Thermoset-Polyester-Composite-Molding-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.00 - 2.10 g/cc	2.00 - 2.10 g/cc	ASTM D792
Bulk Factor	1.0	1.0	ASTM D1895
Filler Content	8.0 %	8.0 %	Glass
Water Absorption	0.10 % @Time 86400 sec	0.10 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage	0.00050 - 0.0030 cm/cm	0.00050 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	40 - 50	40 - 50	ASTM D2583
Tensile Strength	27.6 - 34.5 MPa	4000 - 5000 psi	ASTM D638
Flexural Strength	68.9 - 82.7 MPa	10000 - 12000 psi	ASTM D790
Flexural Modulus	8.27 - 10.3 GPa	1200 - 1500 ksi	ASTM D790
Compressive Strength	89.6 - 110 MPa	13000 - 16000 psi	ASTM D695
Shear Strength	27.6 - 34.5 MPa	4000 - 5000 psi	ASTM D732
Izod Impact, Notched	1.07 - 2.14 J/cm	2.00 - 4.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	>= 260 Â°C	>= 500 Â°F	ASTM D648
Flammability, UL94	V-0	V-0	
	5VB	5VB	

Electrical Properties	Metric	English	Comments
Dielectric Strength	13.8 kV/mm	350 kV/in	ASTM D149
Arc Resistance	>= 240 sec	>= 240 sec	ASTM D495
Track Resistance	6000 sec	6000 sec	Inclined-Plane Tracking; ASTM D2303

Descriptive Properties	Value	Comments
Listed File E80533	No	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China