

MarkeTech Repton 837 Zirconia + 4.4 mol% Calcia

Category: Ceramic, Oxide, Zirconium Oxide

Material Notes:

Brand 837 features: Good spalling characteristics.REPTON setter tiles, kiln furniture, and special fixtures are lightweight, ridge, and high strength ceramics that resist distortion and spalling, even when thermal cycled many times. They are available with a smooth or a unique textured surface that permits pinpoint contact with the load. Sticking can be eliminated as well as providing a surface that breathes, allowing gasses from the ceramic to escape. Applications include firing ceramic capacitors, SOFCs, PZTs, hard and soft ferrites, co-fired substrates and powdered metals. REPTON is available in a wide range of compositions that include a range of alumina, mullite/alumina, zirconia, cordierite, magnesia, and aluminum titanate.

Order this product through the following link:

http://www.lookpolymers.com/polymer_MarkeTech-Repton-837-Zirconia-44-mol-Calcia.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|--------------|--|
| Bulk Density | 4.20 g/cc | 0.152 lb/in³ | |
| Density | 5.75 g/cc | 0.208 lb/in³ | calculated from bulk density after subtracting pore volume |
| Porosity | 27 % | 27 % | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|-------------|-------------|----------|
| Flexural Strength | >= 18.0 MPa | >= 2610 psi | |

| Thermal Properties | Metric | English | Comments |
|--------------------|---------------------|-------------------------|----------|
| CTE, linear | 8.00 Âμm/m-°C | 4.44 Âμin/in-°F | |
| | @Temperature 300 °C | @Temperature 572 °F | |
| | 8.00 Âμm/m-°C | 4.44 Âμin/in-°F | |
| | @Temperature 900 °C | @Temperature 1650 °F | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|--------|---------|----------|
| CaO | 4.4 % | 4.4 % | |
| ZrO2 | 95.6 % | 95.6 % | |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Spall Resist | 500°C | |

Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China