

## Materion Beryllium Copper Alloy 25 Tube; H (TD04) Temper; up to 9.5 mm o.d. (UNS C17200)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

### Material Notes:

Treatment required for max strength: as supplied  
Tabulated properties apply to products after age hardening. Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Materion-Beryllium-Copper-Alloy-25-Tube-H-TD04-Temper-up-to-95-mm-od-UNS-C17200.php](http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-25-Tube-H-TD04-Temper-up-to-95-mm-od-UNS-C17200.php)

| Physical Properties | Metric    | English                  | Comments |
|---------------------|-----------|--------------------------|----------|
| Density             | 8.36 g/cc | 0.302 lb/in <sup>3</sup> |          |

| Mechanical Properties      | Metric        | English            | Comments |
|----------------------------|---------------|--------------------|----------|
| Hardness, Rockwell B       | 88 - 103      | 88 - 103           |          |
| Tensile Strength, Ultimate | 620 - 900 MPa | 89900 - 131000 psi |          |
| Tensile Strength, Yield    | 510 - 730 MPa | 74000 - 106000 psi |          |
| Elongation at Break        | 8.0 - 30 %    | 8.0 - 30 %         |          |
| Modulus of Elasticity      | 131 GPa       | 19000 ksi          |          |
| Machinability              | 20 %          | 20 %               |          |

| Thermal Properties   | Metric                                     | English                                            | Comments |
|----------------------|--------------------------------------------|----------------------------------------------------|----------|
| CTE, linear          | 17.0 $\mu\text{m/m-}^{\circ}\text{C}$      | 9.44 $\mu\text{in/in-}^{\circ}\text{F}$            |          |
|                      | @Temperature 20.0 - 200 $^{\circ}\text{C}$ | @Temperature 68.0 - 392 $^{\circ}\text{F}$         |          |
| Thermal Conductivity | 105 W/m-K                                  | 729 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$ |          |
| Melting Point        | 870 - 980 $^{\circ}\text{C}$               | 1600 - 1800 $^{\circ}\text{F}$                     |          |
| Solidus              | 870 $^{\circ}\text{C}$                     | 1600 $^{\circ}\text{F}$                            |          |
| Liquidus             | 980 $^{\circ}\text{C}$                     | 1800 $^{\circ}\text{F}$                            |          |

| Component Elements Properties | Metric        | English       | Comments |
|-------------------------------|---------------|---------------|----------|
| Beryllium, Be                 | 1.8 - 2.0 %   | 1.8 - 2.0 %   |          |
| Co + Ni                       | $\geq 0.20$ % | $\geq 0.20$ % |          |
| Co + Ni + Fe                  | $\leq 0.60$ % | $\leq 0.60$ % |          |

| Component Elements Properties | Metric     | English    | Comments |
|-------------------------------|------------|------------|----------|
| Lead, Pb                      | <= 0.020 % | <= 0.020 % |          |

| Electrical Properties  | Metric                           | English                          | Comments                 |
|------------------------|----------------------------------|----------------------------------|--------------------------|
| Electrical Resistivity | 0.00000910 -<br>0.0000115 ohm-cm | 0.00000910 -<br>0.0000115 ohm-cm | 15-19% IACS Conductivity |

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)  
Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)  
Tel : +86 021-51131842  
Mobile : +86 13061808058  
Skype : lookpolymers  
Address : United North Road 215,Fengxian District, Shanghai City,China