

Menzolit MenzolitÂ® BMC 2300 Unsaturated Polyester UP

Category : Polymer , Thermoset , Polyester, TS , Thermoset Polyester Glass Filled BMC

Material Notes:

BMC 2300 is a special BMC with exceptional high fire retardancy. The glass content is set to a level that provides sufficient mouldability with high strength and stiffness properties. Fire retardancy is exceptionally high and the material is not burnable. The high fire retardancy makes it especially suited for switch gear components, for high voltage and high current applications. Information Provided by Menzolit

Order this product through the following link:

http://www.lookpolymers.com/polymer_Menzolit-Menzolit-BMC-2300-Unsaturated-Polyester-UP.php

Physical Properties	Metric	English	Comments
Density	1.90 g/cc	0.0686 lb/inÂ³	ISO 1183
Water Absorption	<= 0.50 %	<= 0.50 %	ISO 62
Linear Mold Shrinkage	0.00080 cm/cm	0.00080 in/in	ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	31.0 MPa @Temperature 22.0 Â°C	4500 psi @Temperature 71.6 Â°F	25mm flat samples, compression moulded; ISO 527-4
Tensile Strength, Yield	31.0 MPa @Temperature 22.0 Â°C	4500 psi @Temperature 71.6 Â°F	25mm flat samples, compression moulded; ISO 527-4
Elongation at Yield	0.00 %	0.00 %	tensile rupture strain; ISO 527-4
Modulus of Elasticity	13.0 GPa	1890 ksi	25mm flat samples, compression moulded; ISO 527-4
Flexural Strength	96.0 MPa @Temperature 22.0 Â°C	13900 psi @Temperature 71.6 Â°F	25 mm wide 100 mm long, flat samples; ISO 14125
Flexural Modulus	10.0 GPa @Temperature 22.0 Â°C	1450 ksi @Temperature 71.6 Â°F	25 mm wide 100 mm long, flat samples; ISO 14125
Poissons Ratio	0.30	0.30	
Shear Modulus	5.00 GPa	725 ksi	in plane
Charpy Impact, Notched	2.30 J/cmÂ²	10.9 ft-lb/inÂ²	ISO 179

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

CTE linear Thermal Properties	10.0 Åum/m-Å°C Metric	5.56 Åuin/in-Å°F English	ISO 11359-2 Comments
Specific Heat Capacity	1.10 J/g-Å°C	0.263 BTU/lb-Å°F	
Thermal Conductivity	0.700 W/m-K	4.86 BTU-in/hr-ftÅ²-Å°F	
Maximum Service Temperature, Air	155 Å°C	311 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	>= 150 Å°C	>= 302 Å°F	ISO 75-2
Minimum Service Temperature, Air	-40.0 Å°C	-40.0 Å°F	
Glass Transition Temp, Tg	134 Å°C	273 Å°F	ISO 11357-2
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	
Oxygen Index	43 %	43 %	ISO 4589-2
Glow Wire Test	960 Å°C	1760 Å°F	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1
Dissipation Factor	0.010	0.010	IEC 60250
Arc Resistance	>= 180 sec	>= 180 sec	ASTM D495
Comparative Tracking Index	600 V	600 V	IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 150 Å°C	275 - 302 Å°F	Injection moulding, matched metal die

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China