

Menzolit Menzolit® SMC 0190 Unsaturated Polyester UP

Category : Polymer , Thermoset , Polyester, TS , Thermoset Polyester Glass SMC

Material Notes:

SMC 0190 is a general purpose SMC for applications in the field of electrical industry. Typical applications are housings, covers, wire distribution boxes and metering cabinets. The material meets the demands of DIN 16913 and is classified as type 834 (834.5) regarding mechanical properties. The flammability meets the demands of standard UL 94 category V0. For grey tones, a certificate (yellow-card) is available on request. The glass content is on a level that combines good mouldability with good mechanical properties regarding strength and stiffness. Information Provided by Menzolit

Order this product through the following link:

http://www.lookpolymers.com/polymer_Menzolit-Menzolit-SMC-0190-Unsaturated-Polyester-UP.php

Physical Properties	Metric	English	Comments
Density	1.70 g/cc	0.0614 lb/in ³	ISO 1183
Water Absorption	<= 0.50 %	<= 0.50 %	ISO 62
Linear Mold Shrinkage	0.0015 cm/cm	0.0015 in/in	ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	66.0 MPa @Temperature 22.0 °C	9570 psi @Temperature 71.6 °F	25mm flat samples, compression moulded; ISO 527-4
Tensile Strength, Yield	66.0 MPa @Temperature 22.0 °C	9570 psi @Temperature 71.6 °F	25mm flat samples, compression moulded; ISO 527-4
Elongation at Yield	0.00 %	0.00 %	tensile rupture strain; ISO 527-4
Modulus of Elasticity	11.0 GPa	1600 ksi	25mm flat samples, compression moulded; ISO 527-4
Flexural Strength	158 MPa @Temperature 22.0 °C	22900 psi @Temperature 71.6 °F	25 mm wide 100 mm long, flat samples; ISO 14125
Flexural Modulus	10.0 GPa @Temperature 22.0 °C	1450 ksi @Temperature 71.6 °F	25 mm wide 100 mm long, flat samples; ISO 14125
Poissons Ratio	0.30	0.30	
Shear Modulus	4.20 GPa	609 ksi	in plane
Charpy Impact, Notched	7.10 J/cm ²	33.8 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear	12.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	6.67 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
Specific Heat Capacity	1.10 J/g $\cdot\text{Å}^\circ\text{C}$	0.263 BTU/lb $\cdot\text{Å}^\circ\text{F}$	
Thermal Conductivity	0.700 W/m-K	4.86 BTU-in/hr-ft $\text{Å}^2\cdot\text{Å}^\circ\text{F}$	
Maximum Service Temperature, Air	165 $\text{Å}^\circ\text{C}$	329 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	$\geq 200 \text{ Å}^\circ\text{C}$	$\geq 392 \text{ Å}^\circ\text{F}$	ISO 75-2
Minimum Service Temperature, Air	-40.0 $\text{Å}^\circ\text{C}$	-40.0 $\text{Å}^\circ\text{F}$	
Glass Transition Temp, Tg	170 $\text{Å}^\circ\text{C}$	338 $\text{Å}^\circ\text{F}$	ISO 11357-2
Flammability, UL94	V-0 @Thickness 3.00 mm	V-0 @Thickness 0.118 in	
Oxygen Index	32 %	32 %	ISO 4589-2
Glow Wire Test	960 $\text{Å}^\circ\text{C}$	1760 $\text{Å}^\circ\text{F}$	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
Dielectric Strength	24.0 kV/mm	610 kV/in	IEC 60243-1
Dissipation Factor	0.010	0.010	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 150 $\text{Å}^\circ\text{C}$	275 - 302 $\text{Å}^\circ\text{F}$	Compression moulding, matched metal die

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China