

Menzolit Menzolit® SMC 0900 Unsaturated Polyester UP

Category : Polymer , Thermoset , Polyester, TS , Thermoset Polyester Glass SMC

Material Notes:

SMC 0900 is a special SMC for use within a chemical aggressive environment. The glass level is selected to combine good mouldability with good strength and stiffness properties. The product is especially suitable for components or housings which are being used in an chemical aggressive environment. Within such an environment temperature, temperature cycle and chemistry play a very important roll. Since this environment is very difficult to describe, we recommend that the user consults our chemical resistance list and contacts our technical service team prior to use. Typical applications are pumps, armatures and housings within chemical plants or offshore platforms. Information Provided by Menzolit

Order this product through the following link:

http://www.lookpolymers.com/polymer_Menzolit-Menzolit-SMC-0900-Unsaturated-Polyester-UP.php

Physical Properties	Metric	English	Comments
Density	1.70 g/cc	0.0614 lb/in ³	ISO 1183
Water Absorption	<= 0.30 %	<= 0.30 %	ISO 62
Linear Mold Shrinkage	0.00080 cm/cm	0.00080 in/in	ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	76.0 MPa @Temperature 22.0 °C	11000 psi @Temperature 71.6 °F	25mm flat samples, compression moulded; ISO 527-4
Tensile Strength, Yield	76.0 MPa @Temperature 22.0 °C	11000 psi @Temperature 71.6 °F	25mm flat samples, compression moulded; ISO 527-4
Elongation at Yield	0.00 %	0.00 %	tensile rupture strain; ISO 527-4
Modulus of Elasticity	11.0 GPa	1600 ksi	25mm flat samples, compression moulded; ISO 527-4
Flexural Strength	166 MPa @Temperature 22.0 °C	24100 psi @Temperature 71.6 °F	25 mm wide 100 mm long, flat samples; ISO 14125
Flexural Modulus	9.00 GPa @Temperature 22.0 °C	1310 ksi @Temperature 71.6 °F	25 mm wide 100 mm long, flat samples; ISO 14125
Poissons Ratio	0.30	0.30	
Shear Modulus	4.20 GPa	609 ksi	in plane
Charpy Impact, Notched	7.50 J/cm ²	35.7 ft-lb/in ²	ISO 179

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
CTE, linear	12.0 $\mu\text{m/m-}^{\circ}\text{C}$	6.67 $\mu\text{in/in-}^{\circ}\text{F}$	ISO 11359-2
Specific Heat Capacity	1.10 J/g- $^{\circ}\text{C}$	0.263 BTU/lb- $^{\circ}\text{F}$	
Thermal Conductivity	0.700 W/m-K	4.86 BTU-in/hr-ft 2 - $^{\circ}\text{F}$	
Maximum Service Temperature, Air	140 $^{\circ}\text{C}$	284 $^{\circ}\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	≥ 200 $^{\circ}\text{C}$	≥ 392 $^{\circ}\text{F}$	ISO 75-2
Minimum Service Temperature, Air	-40.0 $^{\circ}\text{C}$	-40.0 $^{\circ}\text{F}$	
Glass Transition Temp, Tg	125 $^{\circ}\text{C}$	257 $^{\circ}\text{F}$	ISO 11357-2
Flammability, UL94	V-0 @Thickness 3.00 mm	V-0 @Thickness 0.118 in	
Oxygen Index	30 %	30 %	ISO 4589-2
Glow Wire Test	960 $^{\circ}\text{C}$	1760 $^{\circ}\text{F}$	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
Dielectric Strength	24.0 kV/mm	610 kV/in	IEC 60243-1
Dissipation Factor	0.010	0.010	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 150 $^{\circ}\text{C}$	275 - 302 $^{\circ}\text{F}$	Compression moulding, matched metal die

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China