

Mitsubishi Xantar® G8F 23 UR Polycarbonate-40% Glass Reinforced

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 40% Glass Filled

Material Notes:

Xantar® materials are engineered for performance, consistency and reliability. This makes Xantar® resins ideal for interior automotive components, electrical equipment and consumer appliances where quality is a key requirement. The Xantar® range includes: clear and tinted grades for transparent applications reinforced materials Flame retardant and halogen free types lubricated materials for added wear resistance Mitsubishi Engineering Plastics acquired the Xantar® product line from DSM in 2010.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mitsubishi-Xantar-G8F-23-UR-Polycarbonate-40-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.52 g/cc	0.0549 lb/in ³	ISO 1183
Water Absorption	0.23 %	0.23 %	Sim. to ISO 62
Viscosity Test	48 cm ³ /g	48 cm ³ /g	Limiting Viscosity Number; ISO 1628-4
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0030 cm/cm	0.0030 in/in	ISO 294-4
Melt Flow	4.56 g/10 min @Load 1.20 kg, Temperature 300 °C	4.56 g/10 min @Load 2.65 lb, Temperature 572 °F	Calculated from Volume Flow Rate of 3 cm ³ /10min.; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	93	93	ISO 2039-2
Tensile Strength at Break	135 MPa	19600 psi	ISO 527-1/-2
Elongation at Break	1.5 %	1.5 %	ISO 527-1/-2
Tensile Modulus	10.5 GPa	1520 ksi	ISO 527-1/-2
Flexural Strength	160 MPa	23200 psi	ISO 178
Flexural Modulus	8.50 GPa	1230 ksi	ISO 178
Izod Impact, Notched (ISO)	10.0 kJ/m ² @Temperature 23.0 °C	4.76 ft-lb/in ² @Temperature 73.4 °F	ISO 180/4A

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 µm/m-°C	11.1 µin/in-°F	ISO 11359-1/-2

Thermal Properties	@Temperature 20.0 Metric °C	@Temperature 68.0 °F English °F	Comments
Maximum Service Temperature, Air	125 Â°C	257 Â°F	Ball Pressure Temperature; IEC 60695-10-2
Deflection Temperature at 1.8 MPa (264 psi)	145 Â°C	293 Â°F	ISO 75-1/-2
Vicat Softening Point	153 Â°C	307 Â°F	50Â°C/h 50N; ISO 306
UL RTI, Electrical	130 Â°C	266 Â°F	UL 746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	130 Â°C	266 Â°F	UL 746B
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical with Impact	125 Â°C	257 Â°F	UL 746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	130 Â°C	266 Â°F	UL 746B
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical without Impact	125 Â°C	257 Â°F	UL 746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	130 Â°C	266 Â°F	UL 746B
	@Thickness 3.00 mm	@Thickness 0.118 in	
Flammability, UL94	V-0	V-0	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	IEC 60695-11-10
	@Thickness 3.00 mm	@Thickness 0.118 in	
Oxygen Index	37 %	37 %	ISO 4589-1/-2
Glow Wire Test	850 Â°C	1560 Â°F	Glow Wire Ignition Temperature; IEC 60695-2-13
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	875 Â°C	1610 Â°F	Glow Wire Ignition Temperature; IEC 60695-2-13
	@Thickness 3.00 mm	@Thickness 0.118 in	
	960 Â°C	1760 Â°F	Glow Wire Flammability Index; IEC 60695-2-12
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	960 Â°C	1760 Â°F	Glow Wire Flammability Index; IEC 60695-2-12
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	IEC 60093
Surface Resistance	$\geq 1.00 \times 10^{15}$ ohm	$\geq 1.00 \times 10^{15}$ ohm	IEC 60093
Dielectric Constant	3.4	3.4	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	3.4	3.4	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	29.0 kV/mm	737 kV/in	IEC 60243-1
Dissipation Factor	0.00090	0.00090	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0090	0.0090	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	200 V	200 V	IEC 60112
	175 - 249 V	175 - 249 V	PLC 3; UL 746A

Descriptive Properties	Value	Comments
Flame Retardant	Yes	
Flame Retarding Agent	Yes	
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
Light stabilized or stable to light	Yes	
Release Agent	Yes	
U.V. stabilized or stable to weather	Yes	
With Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China