

## Momentive Performance Materials Silplusâ, \$ 80 EX Heat Cured Rubber - Extrusion

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE), Silicone, Silicone Rubber

## **Material Notes:**

Heat cured rubber is a high consistency product that can be molded, extruded or calendered using conventional rubber processing equipment to meet a wide range of cost, durability and performance standards. Silplus 80 EX is a peroxide curable, extrusion grade, silicone elastomer.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Momentive-Performance-Materials-Silplus-80-EX-Heat-Cured-Rubber-Extrusion.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	
Tensile Strength	10.0 MPa	1450 psi	
Elongation at Break	440 %	440 %	
Tear Strength	28.0 kN/m	160 pli	Die B

Optical Properties	Metric	English	Comments
Transmission, Visible	20 %	20 %	translucent; thickness unknown

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	FDA Indirect food contact - Rubber articles intended for repeated use - FDA Reg 21CFR177.2600
USP Class VI	Yes	Yes	USP Class VI methods: Intramuscular implantation, intracutaneous injection, & systematic injection

Descriptive Properties	Value	Comments
Appearance	Translucent	
BfR	product is compositionally compliant	Recommendation XV Silicones; post cured (4h/200°C)
ISO10993	yes	7 ISO 10993 tests applicable to "wet" chemicals
Water Regulations	compliant	WRAS



## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China