

Multibase C6-560 Dow-Corning Class VI Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-C6-560-Dow-Corning-Class-VI-Elastomer.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	Relative, no post cure; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	no post cure; ASTM D2240
	58	58	post cured-2 hours at 177 ^o C; ASTM D2240
	59	59	post cured-4 hours at 177 ^o C; ASTM D2240
	59	59	post cured- 8 hours at 177 ^o C; ASTM D2240
Tensile Strength, Ultimate	8.55 MPa	1240 psi	post cured- 8 hours at 177 ^o C; ASTM D412
	8.784 MPa	1274 psi	post cured- 4 hours at 177 ^o C; ASTM D412
	8.798 MPa	1276 psi	post cured- 2 hours at 177 ^o C; ASTM D412
	8.83 MPa	1280 psi	no post cure; ASTM D412
Tensile Strength, Yield	3.96 MPa	575 psi	at 200%, no post cure- press cured for 5 minutes; ASTM D412
	4.21 MPa	610 psi	200%, post cured- 4 hours at 177 ^o C; ASTM D412
	4.27 MPa	619 psi	at 200%, post cured- 2 hours at 177 ^o C; ASTM D412
	4.29 MPa	622 psi	200%, post cured- 8 hours at 177 ^o C; ASTM D412
Elongation at Break	492 %	492 %	post cured- 8 hours at 177 ^o C; ASTM D412
	503 %	503 %	post cured- 2 hours at 177 ^o C; ASTM D412
	518 %	518 %	post cured- 4 hours at 177 ^o C; ASTM D412
	540 %	540 %	no post cure; ASTM D412

Mechanical Properties	Metric	English	Comments
Tear Strength	47.8 kN/m	271 pli	Die B, post cured- 2 hours at 177Â°C; ASTM D624
	49.4 kN/m	282 pli	Die B, post cured- 4 hours at 177Â°C; ASTM D624
	50.7 kN/m	289 pli	Die B, post cured- 8 hours at 177Â°C; ASTM D624
	50.8 kN/m	290 pli	Die B, no post cure; ASTM D624
Compression Set	33 %	33 %	no post cure; ASTM D395

Thermal Properties	Metric	English	Comments
Shrinkage	2.7 %	2.7 %	no post cure

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China