

Multibase Multi-ABS 1030 White

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-ABS-1030-White.php

Physical Properties	Metric	English	Comments
Melt Flow	2.4 g/10 min	2.4 g/10 min	Pellets; ASTM D-1238-94a
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	
	3.14 g/10 min	3.14 g/10 min	Molded Parts; ASTM D-1238-94a
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	29.8 MPa	4320 psi	ASTM D638-95
Elongation at Break	31.8 %	31.8 %	ASTM D638-95
Flexural Strength	47.8 MPa	6930 psi	ASTM D790-95
Flexural Modulus	1.606 GPa	232.9 ksi	RT; ASTM D-790-95
Izod Impact, Notched	2.67 J/cm	5.00 ft-lb/in	ASTM D256-93a
Gardner Impact	10.6 J	7.82 ft-lb	ASTM D5420-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China