

Multibase Multi-Flex® A 2599 TPE Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

This material bonds to polypropylene. Features: Chemical Resistance, Good Colorability, Good Elasticity, High Electrically Insulating Flame Retardant Flexibility, Good Heat Stabilized Ozone Resistant Processability, Good Soft UV Resistance, Good Forms: Pellets Processing Method: Injection Molding Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-A-2599-TPE-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM 792
Linear Mold Shrinkage	0.017 cm/cm	0.017 in/in	ASTM D955
Melt Flow	25 g/10 min @Load 2.16 kg, Temperature 230 °C	25 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	10 seconds; ASTM D2240
Tensile Strength, Yield	4.48 MPa	650 psi	Elastic; ASTM D412
Elongation at Break	700 %	700 %	Elastic; ASTM D412
Tear Strength	16.7 kN/m	95.0 pli	ASTM D624

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	210 °C	410 °F	
Front Barrel Temperature	227 °C	440 °F	
Nozzle Temperature	235 °C	455 °F	
Mold Temperature	51.7 °C	125 °F	
Drying Temperature	51.7 °C	125 °F	
Dry Time	2 - 4 hour	2 - 4 hour	
Injection Pressure	3.45 - 4.83 MPa	500 - 700 psi	
Back Pressure	0.345 MPa	50.0 psi	
Screw Speed	40 rpm	40 rpm	

Descriptive Properties	Value	Comments
Clamp Tonnage	1.5-2.5 tons/in ²	
Injection Rate	Fast	
Suggested Max Regrind	0.5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China