

Multibase Multi-Flex[®] D 3104 TPO Thermoplastic Polyolefin Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyolefin

Material Notes:

Features: Chemical Resistance, Good Paintable Ozone Resistant Thermal Stability, Good Density, Low Tear Strength, Good

Forms: Pellets Processing Method: Injection Molding Uses: Automotive Applications Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-D-3104-TPO-Thermoplastic-Polyolefin-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.902 g/cc	0.902 g/cc	ASTM 792
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955
Melt Flow	3.0 g/10 min @Load 2.16 kg, Temperature 230 °C	3.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	39	39	10 seconds; ASTM D2240
Tensile Strength, Yield	15.9 MPa	2300 psi	Elastic; ASTM D412
Elongation at Break	540 %	540 %	Elastic; ASTM D412
Flexural Modulus	0.193 GPa	28.0 ksi	ASTM D790
Tear Strength	84.1 kN/m	480 pli	ASTM D624

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	177 - 199 °C	350 - 390 °F	
Middle Barrel Temperature	199 - 221 °C	390 - 430 °F	
Front Barrel Temperature	221 - 232 °C	430 - 450 °F	
Nozzle Temperature	6.11 - 232 °C	43.0 - 450 °F	
Melt Temperature	232 °C	450 °F	
Mold Temperature	37.8 °C	100 °F	

Descriptive Properties	Value	Comments
Clamp Tonnage	2-4 tons/in ²	
Screw L/D Ratio	20:1	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China