

Multibase Multi-Flex® TPE A 7204 LC BLK

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-7204-LC-BLK.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in³	ASTM D792
Melt Flow	4.0 g/10 min	4.0 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72	72	10 sec; ASTM D-2240
Tensile Strength, Ultimate	7.60 MPa	1100 psi	ASTM D412
Elongation at Break	800 %	800 %	ASTM D412
Tear Strength	35.0 kN/m	200 pli	ASTM D624
Compression Set	19 %	19 %	for 70 hours at 23°C; ASTM 395
	29 %	29 %	for 70 hours at 70°C; ASTM 395
	@Temperature 70.0 °C	@Temperature 158 °F	
	45 %	45 %	70 hours at 100°C; ASTM 395
	@Temperature 100 °C	@Temperature 212 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China