

Multibase Multi-Flex® TPE G 7410 NAT

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The following properties were obtained from the Shell Kraton G 7410 and the Multibase 7410 products. Multi-Flex TPE contains Kraton™
G.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-G-7410-NAT.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in³	ASTM D792
Melt Flow	2.0 g/10 min	2.0 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	66	66	10 sec; ASTM D-2240
Tensile Strength, Ultimate	10.7 MPa	1550 psi	ASTM D412
Elongation at Break	690 %	690 %	ASTM D412
Tear Strength	42.4 kN/m	242 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China