

Multibase Multi-Pro® 5002 CU Natural Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Forms: Pellets Processing Methods: Injection Molding Features: Gloss, Low Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Pro-5002-CU-Natural-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in³	ASTM D792
Linear Mold Shrinkage	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	ASTM D955
Melt Flow	2.25 g/10 min @Load 2.16 kg, Temperature 230 °C	2.25 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	19.3 MPa	2800 psi	ASTM D638
Elongation at Break	900 %	900 %	ASTM D638
Flexural Strength	31.0 MPa	4500 psi	ASTM D790
Flexural Modulus	2.38 GPa	345 ksi	Method I (3 point load), Procedure B); ASTM D790
Izod Impact, Notched	NB	NB	73°F; ASTM D256
Gardner Impact	22.60 J	16.67 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	120 °C	248 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China