

Mytex Polymers AS66K-01 Polypropylene, Talc filled, Compounded

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Description: Talc filled compounded polypropylene produced for automotive interior applications using Mytex® Technology.Key

Applications: General purpose interiorInformation provided by Mytex Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mytex-Polymers-AS66K-01-Polypropylene-Talc-filled-Compounded.php

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	50	50	ASTM D785
Tensile Strength, Yield	19.0 MPa	2760 psi	50 mm/min; ASTM D638
Flexural Modulus	1.30 GPa	189 ksi	Tangent; 1.3 mm/min; ASTM D790
Izod Impact, Notched	6.50 J/cm @Temperature 23.0 °C	12.2 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 °C	194 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China