

NEU NeuSoft™ 602-60A Ester TPU / SBC blend

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_NEU-NeuSoft-602-60A-Ester-TPU-SBC-blend.php

Physical Properties	Metric	English	Comments
Density	1.073 g/cc	0.03876 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	
Tensile Strength at Break	20.0 MPa	2900 psi	
Tensile Stress	2.69 MPa	390 psi	
	@Strain 100 %	@Strain 100 %	
	3.38 MPa	490 psi	
	@Strain 300 %	@Strain 300 %	
Elongation at Break	949 %	949 %	
Tear Strength	53.8 kN/m	307 pli	Die C
Compression Set	18.7 %	18.7 %	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.010 %	<= 0.010 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China