

NIZHNEKAMSKNEFTEKHIM PE 4020R (20405) Linear Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Information provided by manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PE-4020R-20405-Linear-Low-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.918 - 0.922 g/cc	0.0332 - 0.0333 lb/in ³	Base Resin; ASTM D1505
Melt Flow	4.0 - 6.0 g/10 min	4.0 - 6.0 g/10 min	ASTM D1283/L
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	
	120 - 180 g/10 min	120 - 180 g/10 min	Flow@21.6kg/Flow@2.16kg ratio < 30; ASTM D1283
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Flexural Modulus	>= 0.400 GPa	>= 58.0 ksi	ASTM D790
Izod Impact, Notched	>= NB	>= NB	ASTM D256
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China