

NIZHNEKAMSKNEFTEKHIM PE 6753G (526H7) High Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Information provided by manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PE-6753G-526H7-High-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.950 - 0.954 g/cc	0.0343 - 0.0345 lb/in ³	Base Resin; ASTM D1505
Melt Flow	0.60 - 0.80 g/10 min	0.60 - 0.80 g/10 min	ASTM D1283/L
	@Load 5.00 kg, Temperature 190 °C	@Load 11.0 lb, Temperature 374 °F	
	42 - 56 g/10 min	42 - 56 g/10 min	Flow@21.6kg/Flow@2.16kg ratio > 70; ASTM D1283
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China