

NOVA Chemicals Novapol® PF-Y821-BP Butene LLDPE Film Resin

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Butene, Film

Material Notes:

Film Properties. Features: Good stiffness and machinability, intended for narrow die gaps. Applications: General purpose packaging, bags requiring moderate clarity, bread bags. Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Novapol-PF-Y821-BP-Butene-LLDPE-Film-Resin.php

Physical Properties	Metric	English	Comments
Density	0.921 g/cc	0.0333 lb/in ³	ASTM D792
Thickness	38.1 microns	1.50 mil	
Melt Flow	0.80 g/10 min @Load 2.16 kg, Temperature 190 °C	0.80 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	10.0 MPa	1450 psi	ASTM D882
Film Tensile Strength at Yield, TD	10.0 MPa	1450 psi	ASTM D882
Film Elongation at Break, MD	660 %	660 %	ASTM D882
Film Elongation at Break, TD	730 %	730 %	ASTM D882
Secant Modulus, MD	0.190 GPa	27.6 ksi	ASTM D882
Secant Modulus, TD	0.230 GPa	33.4 ksi	ASTM D882
Coefficient of Friction	<= 0.25	<= 0.25	ASTM D1894
Elmendorf Tear Strength, MD	5.10 g/micron	130 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	10.2 g/micron	259 g/mil	ASTM D1922
Dart Drop	3.70 g/micron	94.0 g/mil	F 50; ASTM D1709/A
Film Tensile Strength at Break, MD	30.0 MPa	4350 psi	ASTM D882
Film Tensile Strength at Break, TD	25.0 MPa	3630 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	11 % @Thickness 0.0250 mm	11 % @Thickness 0.000984 in	ASTM D1003

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

95.1 TMM, ASTM D1894

Processing Properties	Metric	English	Comments
Melt Temperature	195 - 220 °C	383 - 428 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China