

NOVA Chemicals Novapol® TR-0338-UI Hexene MDPE Rotational Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , MDPE , Medium Density Polyethylene (MDPE), Molded

Material Notes:

Excellent low temperature impact properties, Excellent ESCR, Good stiffness, Wide processing window
Applications: General purpose custom molding, Chemical containers, IBCs, Fish boxes, Septic tanks, Agricultural storage tanks
Additives: Processing antioxidants, UV stabilizers
Information provided by NOVA Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Novapol-TR-0338-UI-Hexene-MDPE-Rotational-Molding-Resin.php

Physical Properties	Metric	English	Comments
Density	0.938 g/cc	0.0339 lb/in ³	ASTM D792
ESCR 100% Igepal®	>= 1000 hour @Temperature 50.0 °C	>= 1000 hour @Temperature 122 °F	F ₅₀ ; Condition A, From compression molded specimens; ASTM D1693
ESCR 10% Igepal®	110 hour @Temperature 50.0 °C	110 hour @Temperature 122 °F	F ₅₀ ; Condition A, From compression molded specimens; ASTM D1693
Melt Flow	3.5 g/10 min @Load 2.16 kg, Temperature 190 °C	3.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	20.6 MPa @Thickness 3.17 mm	2990 psi @Thickness 0.125 in	Type IV specimen, 2" per minute test speed, rotomolded samples; ASTM D638
Flexural Modulus	0.860 GPa	125 ksi	1% Strain Value from rotomolded samples; ASTM D790
Impact Test	70.0 J @Thickness 3.17 mm, Temperature -40.0 °C	51.6 ft-lb @Thickness 0.125 in, Temperature -40.0 °F	rotomolded; ARM Method
	220 J @Thickness 6.35 mm, Temperature -40.0 °C	162 ft-lb @Thickness 0.250 in, Temperature -40.0 °F	rotomolded; ARM Method

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	49.0 °C	120 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	38.0 °C	100 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China