

NOVA Chemicals Sclair® 2315 LLDPE Injection Molding Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

Material Notes:

Features: Low odor, low warpage, fast cycling, high surface gloss, permits light weight lid design, low temperature impact excellent. Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Sclair-2315-LLDPE-Injection-Molding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.931 g/cc	0.0336 lb/in ³	ASTM D792
Melt Flow	63 g/10 min @Load 2.16 kg, Temperature 190 °C	63 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	56	56	ASTM D2240
Tensile Strength, Yield	14.0 MPa	2030 psi	50 mm/min; ASTM D638
	17.0 MPa	2470 psi	500 mm/min; ASTM D638
Flexural Modulus	0.520 GPa	75.4 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	100 °C	212 °F	ASTM D1525
Brittleness Temperature	<= -60.0 °C	<= -76.0 °F	ASTM D696

Processing Properties	Metric	English	Comments
Melt Temperature	170 - 260 °C	338 - 500 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China