

NOVA Chemicals Sclair® 59F HDPE Blow Molding Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

Material Notes:

Features: High impact resistance, good stiffness, moderate ESCR. Applications: Food packaging, small parts (HIC), oil bottles. Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Sclair-59F-HDPE-Blow-Molding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in ³	ASTM D792
Environmental Stress Crack Resistance	75 hour	75 hour	F50, Condition A, ASTM D1693, 100% Igepal
Melt Flow	0.29 g/10 min @Load 2.16 kg, Temperature 190 °C	0.29 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	67	67	ASTM D2240
Tensile Strength, Yield	31.5 MPa	4570 psi	ASTM D638
Elongation at Break	1000 %	1000 %	ASTM D638
Flexural Modulus	1.31 GPa	190 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	126 °C	259 °F	ASTM D1525
Brittleness Temperature	<= -70.0 °C	<= -94.0 °F	ASTM D696

Processing Properties	Metric	English	Comments
Melt Temperature	160 - 205 °C	320 - 401 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China