

NYCOA 512 PA 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced, Flame Retardant

Material Notes:

UL and NSF rated nucleated general purpose molding gradeInformation provided by NYCOA, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NYCOA-512-PA-6.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Water Absorption	1.7 %	1.7 %	ASTM D570
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	86.0 MPa	12500 psi	ASTM D638
Elongation at Break	>= 40 %	>= 40 %	ASTM D638
Flexural Yield Strength	99.0 MPa	14400 psi	ASTM D790
Flexural Modulus	2.656 GPa	385.2 ksi	ASTM D790
Izod Impact, Notched	0.460 J/cm	0.862 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ASTM D789
Deflection Temperature at 1.8 MPa (264 psi)	68.0 °C	154 °F	ASTM D648
Flammability, UL94	V-2 @Thickness 0.700 mm	V-2 @Thickness 0.0276 in	

Processing Properties	Metric	English	Comments
Processing Temperature	250 °C	482 °F	
Rear Barrel Temperature	225 °C	437 °F	
Middle Barrel Temperature	230 °C	446 °F	
Front Barrel Temperature	250 °C	482 °F	

Nozzle Temperature Processing Properties	250 °C Metric	482 °F English	Comments
Mold Temperature	80.0 °C	176 °F	
Drying Temperature	76.0 °C	169 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China